

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

Patent Abstracts of Japan

PUBLICATION NUMBER : 10046021
PUBLICATION DATE : 17-02-98

APPLICATION DATE : 07-08-96
APPLICATION NUMBER : 08226054

APPLICANT : NIPPON G II PLAST KK;

INVENTOR : SAITO AKIHIRO;

INT.CL. : C08L 69/00 C08L 69/00 A47G 19/00 C08K 5/09 C08K 5/10 C08L 67/02 C08L 67/02

TITLE : TABLEWARE EXCELLENT IN DETERGENT RESISTANCE

ABSTRACT : PROBLEM TO BE SOLVED: To provide the subject tableware excellent in food contamination, crack and detergent resistances by using a resin composition comprising an aromatic polycarbonate, a polyester, a polyester carbonate and a transesterification catalyst.

SOLUTION: The tableware is obtained by using a resin composition comprising (A) 40-97 pts.wt. aromatic polycarbonate, (B) 1-45 pts.wt. polyester, (C) 0-60 pts.wt. polyester carbonate, (D) 0-0.5 pt.wt. transesterification catalyst (e.g. a Lewis acid catalyst such as tin acetate) and (E) 0-30 pts.wt. stabilizer (e.g. a protonic acid such as acetic acid). An aromatic polycarbonate prepared from 2,2-bis(4-hydroxyphenyl)propane and diphenyl carbonate as raw materials is preferred as the component A and a polyester obtained from an aromatic dicarboxylic acid and an alkylene diol such as polyethylene terephthalate is preferred as the component B. An aromatic polyester carbonate comprising a carbonic acid residue, an aromatic dicarboxylic acid and an aromatic dihydroxy residue is preferred as the component C.

COPYRIGHT: (C)1998,JPO